Technical data sheet



Merbenit 2K60

Merbenit 2K60 is a permanently elastic 2-component adhesive with a very fast strength build-up and very good adhesion properties, especially on synthetics which are difficult to bond.

Product advantages

- Fast strength build-up, handling strength achieved after 30 minutes
- Compatible with paints
- Simple processing
- High elasticity, good mechanical strength
- Corrosion protecting
- Free of solvents, isocyanates and silicones
- Odourless
- Non-corrosive on surfaces
- Vibration absorbing
- Very wide adhesion range
- Very good sealing properties

Technical data

| Shore-A-hardness, DIN 53505 | 48 |
|---|-------------------------------|
| Modulus elongation at 100%, | ca. 2.0 N/mm² |
| DIN 53504 S2 | |
| Elongation at break, DIN 53504 S2 | ca. 150% |
| Tensile strength after 1h, DIN 53504 S2 | ca. 1.3 N/mm² |
| Tensile strength after 7d, DIN 53504 S2 | ca. 3.0 N/mm² |
| Consistency | slightly thixotropic |
| Tooling time | max. 4 min. |
| Density | 1.37 ± 0.05 g/cm ³ |
| Volume change, DIN EN ISO 10563 | ≤8% |
| Temperature resistance after curing | - 40 °C to + 90 °C |
| Application temperature | + 5 °C to + 40 °C |
| Temperature of the substrate | + 5 °C to + 40 °C |
| Shear strength | ca. 3.0 N/mm² |


All measurements were performed under normal conditions (23 $^\circ\mathrm{C}$ and 50 % relative humidity).

Application

Flexible bonding in the areas of metal, apparatus and machine construction, plastics technology, air-conditioning and ventilation systems, car body, wagon, vehicle and container construction. Thanks to fast crosslinking it is possible to bond parts in continous working process. The neutral polymerisation allows a connection without thermal or chemical pre-treatment of the assembly parts. Counterbalancing tolerances.

Substrate range

Suitable materials are metals, powder-coated, varnished, galvanised, anodised, chromed or hot zinc dipped surfaces, various plastics, ceramics, stone, concrete and wood. Due to the large variety of different plastics and compositions as well as materials which are susceptible cracks, preliminary tests are recommended.



Technical data sheet Merbenit 2K60

Substrate preparation

To achieve reproductible results the substrate has to be pre-treated according to the state of technology. For application the surface has to be clean, durable and free of dust, oil and grease. All undefined surfaces must be removed using suitable methods. Apply the adhesive/sealant promptly to the prepared surface. Depending on the substrate and the expected requirements a mechanical or chemical pre-treatment is recommended respectively cleaning with rubbing alcohol, isopropanol or acetone.

Adhesion promoter

With most materials a good adhesion is achieved even without adhesion promoter. In the case of high moisture influence we recommend our Adhesion Promoter V40 on non-porous materials, Adhesion Promoter V21 on open porous materials. For thermopainted or powder-coated surfaces we recommend our Adhesion Promoter V40. In the case of special plastics an improvement of the adherance can be achieved with Adhesion Promoter V30.

Processing

- Processing out of cartridges:
- Open closure of the cartridge. Place cartridge in proper gun and squeeze until both components are flowing evenly. Wipe off excess. Put the static mixer nozzle and apply the material. Ensure the exiting material has a uniform colour.
- For application by pneumatic gun use a maximum pressure of 3 bar
- Can be applied with automatic dispension equipment
- Depending on the bonding surface, material expansion, tension and mechanical stresses a layer thickness of 1 - 6 mm is recommended
- Mixing ratio 1:1
- Non-cured adhesive can be removed with rubbing alcohol or isopropanol
- Cured adhesive can only be removed mechanically

Paint compatibility

Due to the diversity of varnishes and paints on the market we recommend preliminary tests. Using paints based on alkyd resins may delay the the drying process. After cleaning with acetone joints can be varnished at any time. For burning process the material can be exposed, when fully cured, in short term to elevated temperatures.

Chemical resistance

- Good against water, aliphatic solvents, oils, grease, diluted inorganic acids and alkalis
- Moderate against esters, ketone and aromatics
- Not resistant against concentrated acids and chlorinated hydrocarbons

Colours

- light greyother colours on request
- other colours on request

Packaging

Double cartridges of 2x 200 ml in carton of 15 units

Shelf life and storage conditions

- 12 months from date of production
- Store cool and dry
- Further information on request

Work and environmental safety

Important information about work and environmental safety is available on the material safety data sheet.



Freiburgstrasse 616 CH - 3172 Niederwangen Tel. +41 31 980 48 48 Fax +41 31 980 48 49 info@merz-benteli.ch www.merz-benteli.ch Our information is based on experiences in lab and practice. Their publication occurs, however, without takeover of a liability for damages and losses which are to be put down to these information, as there the practical application conditions are lying outside of the enterprise's control. The user is not released from the necessity to carry out own attempts for the planned applications under practical conditions. Due to the different materials, processing methods and local factors onto which we have no influence, no guarantee – also in patent-legal respect – can be taken over. We recommend therefore sufficient own attempts. By the way we refer to our General Business Conditions. Technical changes reserved. Contents examined and released by merz+benteli ag, CH - Niederwangen/Berne