

# MOLYKOTE® G 67

## Extreme Pressure Grease

### Features

- Excellent protection against fretting corrosion
- Good load-carrying capacity
- High level of protection against wear
- Particularly adhesive

### Composition

- Mineral oil
- Lithium soap
- Adhesion improver
- Solid lubricants

### Applications

Spur gear systems, load chains, settling shims, springs, shaft-hub connection, encapsulated joints, gears, linear motion guides.

### How to use

Clean points of contact. Apply in same way as lubricating greases, using brush, spatula, grease-gun or automatic lubricating device. Suitable for delivery by central lubricating system. In the event of long breaks in service (e.g., overnight), the pressure in the delivery equipment should be relieved. Not to be mixed with other greases.

Because of variation in quality of plastics and elastomers, compatibility tests should be carried out for swelling and shrinkage, stress-crack formation, and changes in strength and hardness.

### Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

### Usable life and storage

When stored at or below 20°C in the original unopened containers, this product has a usable life of 60 months from the date of production.

### Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard <sup>(1)</sup>	Test	Unit	Result
	Color		Beige
<b>Penetration, density, viscosity</b>			
DIN 51 818	NLGI consistency class		1
ISO 2137	Worked penetration	mm/10	310-340
ISO 2811	Density at 20°C	g/ml	1.12
DIN 51 562	Base oil viscosity at 40°C	mm <sup>2</sup> /s	115
<b>Temperature</b>			
	Service temperature	°C	-25 to +120
ISO 2176	Drop point	°C	155
<b>Load-carrying capacity, wear protection, service life</b>			
	Four-ball tester (VKA)		
DIN 51 350 T.4	Weld load	N	4,800
DIN 51 350 T.5	Wear scar under 600 N load	mm	0.75
	Almen-Wieland machine, OK load	N	20,000
	Fretting corrosion - Deyber tester	cycles	>36x10 <sup>6</sup>
<b>Resistance</b>			
DIN 51 808	Oxidation resistance, pressure drop 100 h, 99°C	bar	2.5
<b>Corrosion protection</b>			
DIN 51 802	Emcor method		0-1
<b>Coefficient of friction</b>			
	Steel ball against plastic surface (POM) Ø ball = 12.7 mm, load = 6.3 N, v = 10 mm/s, 24 h	μ	0.08
<b>Oil separation - evaporation</b>			
DIN 51 817 Fed-Standard 791-32-2	Oil separation - standard test 7 days, 40°C	%	4.3

<sup>(1)</sup>DIN: Deutsche Industrie Norm. ISO: International Standardization Organization.

## Packaging

This product is available in 1 kg cans, 400 g cartridges and 5 kg drums.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.  
© 1998-2020 DuPont.*

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.